

Stone commercial name: **KAVALA MARBLE**

Country of origin: Greece

Some typical lab test results:

Water absorption at atmospheric pressure, (EN 13755)	0.1 %
Compressive strength, (EN 1926)	80 Mpa
Flexural strength, (EN 12372)	10.3 Mpa

The tests have been performed on behalf of Dionyssomarble by CERECO S.A laboratory /Greece